



M60 PAINTING/CLEAR FINISHING

110 MASONRY REPAIR/ PAINT: UNPAINTED SURFACES

KEIM LOTEXAN TREATMENT

A siloxane based clear treatment for use on all forms of mineral and cementitious substrates which acts as a water repellent and dust suppresser. Keim Lotexan is optimised for application onto alkali surfaces.

Manufacturer: Keim Mineral Paints Limited, Santok Building, Deer Park Way, Telford, Shropshire TF2 7NA T: 01952 231250 F: 01952 231251 E: sales@keimpaints.co.uk

REFERENCE: KEIM LOTEXAN

Preparation:

Keim Algicide

A non-acid fungicide wash.

Any algae growth should be wire brushed to remove all growths and treated with Keim Algicide, brush applied undiluted and allowed to remain undisturbed for some 3 hours before thoroughly washing off.

All gaps, cracks and holes in the substrate must be filled prior to any treatment. Any suspect mortar jointing should be raked out and re-instated where necessary. Any new/repaired surfaces should be left for a minimum period of 15 days prior to any treatment taking place.

All surfaces must be thoroughly washed down with clean cold water to remove all surface dirt and dust. Ensure all surfaces are clean, sound, wind dry, dust free and free from all surface contaminants.

Application:

Keim Lotexan

A siloxane based waterproofing treatment. Apply the first coat of Keim Lotexan by low-pressure spray, working from the bottom of the substrate upwards, firstly in a horizontal manner. After a period of approximately 10 minutes a further coat should be applied again from bottom to top, this time in a vertical manner, thus ensuring that all facets of the substrate are well coated. It is important that Keim Lotexan is only applied to a dry surface and care is taken to avoid runs, as the material is thin.

The material is contained within a solvent-based carrier (ethanol) and is used with adequate ventilation; where necessary a breathing mask with an organic solvent vapour filter should be used.



IMPORTANT INFORMATION REGARDING STANDARD KEIM SPECIFICATIONS

We have taken every care to ensure that specifications are accurate, if there is any doubt about how to deal with a specific problem or the most suitable products to use, please contact us.

Specifications downloaded from the Keim Mineral Paints website are standard specifications to cover general circumstances and may not be suitable for every situation. Dedicated project specific specifications and product advice can be obtained by contacting sales@keimpaints.co.uk or 01952 231250.

It is essential that each stage of the specification is complied with, including level of preparation and drying times between coats, to ensure the best performance from the system applied. All products should be applied in accordance with the specification and relevant datasheets.

GENERAL INFORMATION RELATING TO THE APPLICATION OF KEIM COATINGS

- All surfaces to be decorated should be free from surface contaminants, sound, dry and dust free.
- Any loose, flaking and unstable material must be identified and then thoroughly removed using stiff brushes and broad bladed scrapers to get back to a sound edge; these edges should then be feathered in. Ensure that any paint materials left remaining and the underlying substrate is sound and adhering well.
- Caution should be taken with the removal of any pre 1960's coatings as they might contain harmful lead.
- Any gloss or shiny surfaces should be thoroughly flatted down using sand or emery paper to create a good key.
- If the surfaces are being chemically stripped, ensure that they are thoroughly washed down of all residues before decoration. Due to the potential for an osmotic drawing reaction which can bring contaminants to the surface, we do not recommend the use of poultice based strippers if surfaces are to be redecorated.
- When airless spraying details of the appropriate nozzle sizes and information about the optimum mesh and filters can be provided on request.
- Any powdery or chalking surfaces will require treatment prior to decoration – contact Keim Mineral Paints to ascertain the appropriate product.
- All materials must be thoroughly mixed beforehand. We do not recommend intermixing packs, however if it is necessary ensure products are thoroughly mixed beforehand to ensure even pigment dispersion before mixing.
- Use only Keim recommended fillers and sealers. Acrylic, resin and gypsum based fillers particularly are not recommended for use with mineral paints.
- Onto new/repared surfaces we would suggest that a drying period of at least 15 days is allowed, prior to the application of Keim.
- Always maintain a wet edge and work materials out well.
- Materials must not be applied at temperatures below 5°C nor those in excess of 30°C, nor if it is raining, or if there is an immediate likelihood of rain
- Keim Mineral Paints should be applied onto wind dry surfaces where the moisture content on or near the surface (to a depth of 5mm approximately) should be no greater than 18% by volume. For on-site purposes a moisture reading may be employed to give a qualitative reading – if the reading is in the green zone decoration may proceed
- Any splashes or spillage should be removed immediately using water - particular note needs to be taken of this in respect of Keim on glass, as it has a slight etching effect if allowed to dry hard
- Clean all brushes and tools immediately in water (some ancillary products containing solvents may require white spirit or turpentine so if in doubt please consult technical data sheets)
- Always store materials upright and secure. Protect from extremes of temperature and store in frost-free conditions
- When ordering reference to the project should be made, to ensure that in the event of re-ordering an exact colour match can be supplied
- Keim Mineral Paints Ltd operates a policy of 'sale and no return' on all goods supplied in good faith