



M60 PAINTING/CLEAR FINISHING

110 MASONRY REPAIR/ PAINT - UNPAINTED ROUGHCAST SURFACES:

KEIM ROYALAN SYSTEM

A silicate based masonry paint system for use on all mineral substrates. It provides long-term decoration and is available in a wide range of standard colour shades. Keim Royalan is specially formulated to withstand extreme climates and harsh weather conditions.

Manufacturer: Keim Mineral Paints Limited, Santok Building, Deer Park Way, Telford, Shropshire TF2 7NA T: 01952 231250 F: 01952 231251 E: sales@keimpaints.co.uk

REFERENCE: KEIM ROYALAN SYSTEM

Preparation:

Keim Algicide

A non-acid fungicide wash. Any algae growth should be wire brushed to remove all growths and treated with Keim Algicide, brush applied undiluted and allowed to remain undisturbed for some 3 hours before thoroughly washing off.

Keim Spachtel

Silicate based filler for all mineral substrates.

Any cracks or where there is a need to equalise the surface should be filled using Keim Spachtel, brush or trowel applied to a pre-wetted surface and dressed back to the required level.

All new/repared surfaces should be left for a minimum period of 15 days prior to decoration using Keim Mineral paints.

All surfaces must be thoroughly washed down with clean cold water to remove all surface dirt and dust. When all surfaces are clean, sound, wind dry, dust free and free from all surface contaminants, decoration using Keim Mineral Paints may proceed.

Keim Royalan Dilution

If necessary highly absorbent or friable surfaces should be treated with Keim Royalan Dilution, a liquid silicate binder, brush applied and left for a minimum period of 12 hours.

Initial Coat(s):

Keim Royalan

Keim Royalan, in the chosen colour, a mineral silicate based paint coat, diluted 40% by weight with Keim Royalan Dilution, a liquid silicate binder, mixed well. Apply by brush, roller or spray and work well into all surfaces.



Finishing coats:

Keim Royalan

After a minimum period of 12 hours apply a final coat of Keim Royalan, in the chosen colour, diluted 5% by weight with Keim Royalan Dilution, a liquid silicate binder. Apply by brush, roller or spray and work well into all surfaces.



IMPORTANT INFORMATION REGARDING STANDARD KEIM SPECIFICATIONS

We have taken every care to ensure that specifications are accurate, if there is any doubt about how to deal with a specific problem or the most suitable products to use, please contact us.

Specifications downloaded from the Keim Mineral Paints website are standard specifications to cover general circumstances and may not be suitable for every situation. Dedicated project specific specifications and product advice can be obtained by contacting sales@keimpaints.co.uk or 01952 231250.

It is essential that each stage of the specification is complied with, including level of preparation and drying times between coats, to ensure the best performance from the system applied. All products should be applied in accordance with the specification and relevant datasheets.

GENERAL INFORMATION RELATING TO THE APPLICATION OF KEIM COATINGS

- All surfaces to be decorated should be free from surface contaminants, sound, dry and dust free.
- Any loose, flaking and unstable material must be identified and then thoroughly removed using stiff brushes and broad bladed scrapers to get back to a sound edge; these edges should then be feathered in. Ensure that any paint materials left remaining and the underlying substrate is sound and adhering well.
- Caution should be taken with the removal of any pre 1960's coatings as they might contain harmful lead.
- Any gloss or shiny surfaces should be thoroughly flatted down using sand or emery paper to create a good key.
- If the surfaces are being chemically stripped, ensure that they are thoroughly washed down of all residues before decoration. Due to the potential for an osmotic drawing reaction which can bring contaminants to the surface, we do not recommend the use of poultice based strippers if surfaces are to be redecorated.
- When airless spraying details of the appropriate nozzle sizes and information about the optimum mesh and filters can be provided on request.
- Any powdery or chalking surfaces will require treatment prior to decoration – contact Keim Mineral Paints to ascertain the appropriate product.
- All materials must be thoroughly mixed beforehand. We do not recommend intermixing packs, however if it is necessary ensure products are thoroughly mixed beforehand to ensure even pigment dispersion before mixing.
- Use only Keim recommended fillers and sealers. Acrylic, resin and gypsum based fillers particularly are not recommended for use with mineral paints.
- Onto new/repared surfaces we would suggest that a drying period of at least 15 days is allowed, prior to the application of Keim.
- Always maintain a wet edge and work materials out well.
- Materials must not be applied at temperatures below 5°C nor those in excess of 30°C, nor if it is raining, or if there is an immediate likelihood of rain
- Keim Mineral Paints should be applied onto wind dry surfaces where the moisture content on or near the surface (to a depth of 5mm approximately) should be no greater than 18% by volume. For on-site purposes a moisture reading may be employed to give a qualitative reading – if the reading is in the green zone decoration may proceed
- Any splashes or spillage should be removed immediately using water - particular note needs to be taken of this in respect of Keim on glass, as it has a slight etching effect if allowed to dry hard
- Clean all brushes and tools immediately in water (some ancillary products containing solvents may require white spirit or turpentine so if in doubt please consult technical data sheets)
- Always store materials upright and secure. Protect from extremes of temperature and store in frost-free conditions
- When ordering reference to the project should be made, to ensure that in the event of re-ordering an exact colour match can be supplied
- Keim Mineral Paints Ltd operates a policy of 'sale and no return' on all goods supplied in good faith